

Durex® Flexlite Select EPS Insulation Board

Drained Expanded Polystyrene Insulation Board Residential Application

Description	Durex® Flexlite Select EPS Insulation Board is a Type I Expanded Polystyrene Insulation Board (as per ULC-S701 and ASTM-C-578) featuring geometrically defined drainage cavities on the back side of the insulation board, intended for use in Durex® Flexlite Select family of EIFS Systems. Durex® Flexlite Select EPS Insulation is supplied in sheets which are 610 mm (2ft) x 1220 mm (4 ft), in thicknesses from 50.8 mm (2") to 152 mm (6") in increments of 12.5 mm (1/2") and available in both Type I EPS and Type II EPS. Durex® Flexlite Select EPS Insulation can be applied over any substrate approved for our Flexlite Select family of EIFS Systems and attached by chemical adhesive bond or by mechanical fasteners as specified. The sheets are not to be applied directly to framing members when part of any Durex® Flexlite Select family of EIFS Systems. All test results given herein, or any of those in our EIFS Systems are specific to use Durex® Flexlite Select EPS Insulation. Substitution voids all tests results and systems warranties offered. Special aesthetic shapes supplied by others are not incorporated in the Durex® EIFS System warranty.
Uses	For use as the exterior insulation in all Durex® Flexlite Select family of EIFS Systems. The use of the expanded polystyrene is governed by the applicable building codes.
Features	<ul style="list-style-type: none"> Moisture does not weaken EPS 10mm drainage cavity GDDC Factor 15% (Geometrically Defined Drainage Cavity) CI factor 0.65 RSI (R 3.9) per inch Type I EPS (Continuous Insulation) CI factor 0.70 RSI (R 4.0) per inch Type II EPS (Continuous Insulation) Thermal protection EPS contains no CFC's, HCFC's or HFC's Chemically inert EPS is a recyclable material Waste to energy safe

TECHNICAL DATA

PHYSICAL PROPERTIES		
Dimensional Tolerances		± 1.6 mm (1/16")
Bowing Tolerances		± 0.8 mm (1/32")
Available Thicknesses		50.8 mm (2") to 152 mm (6") in 12.5 mm (1/2") increments
Material		Type I EPS - 1.0 lb/ft³ (Virgin) Density Expanded Polystyrene Type II EPS - 1.4 lb/ft³ (Virgin) Density Expanded Polystyrene
Coverage		0.74 m² (8 ft²) per board

PERFORMANCE PROPERTIES	METHOD	RESULT
Density	ASTM D1622	1.0 lb/ft³ (16.0 Kg/m³) – Type I EPS 1.4 lb/ft³ (16.0 Kg/m³) – Type II EPS
Thermal Resistance	ASTM C518	3.9 ft² h·°F/BTU – Type I EPS (R-Value / 1" @ 75°F) 0.65 m²·°K/W – Type I EPS (RSI / 25mm @ 24°C) 4.0 ft² h·°F/BTU – Type II EPS (R-Value / 1" @ 75°F) 0.70 m²·°K/W – Type II EPS (RSI / 25mm @ 24°C)
Thermal Resistance	ASTM STP1320	4.6 ft² h·°F/BTU – Type I EPS (R-Value / 1" @ 0°F) 0.81 m²·°K/W – Type I EPS (RSI / 25mm @ -18°C) 4.8 ft² h·°F/BTU – Type II EPS (R-Value / 1" @ 0°F) 0.84 m²·°K/W – Type II EPS (RSI / 25mm @ -18°C)
Compressive Strength	ASTM D1612	12.5 psi (86.0 kPa) at 10% Strain – Type I EPS 22.4 psi (154.6 kPa) at 10% Strain – Type II EPS
Flexural Strength	ASTM C203	27.8 psi (192.0 kPa) – Type I EPS 45.0 psi (310.0 kPa) – Type II EPS
Water Absorption	ASTM D2842	3.8 % (% by volume) – Type I EPS 1.87 % (% by volume) – Type II EPS
Water Vapour Permeance	ASTM E96	282.0 ng/Pa.s.m² (4.95 perms) – Type I EPS 187.23 ng/Pa.s.m² (3.29 perms) – Type II EPS
Dimensional Stability	ASTM D2126	-1.5 % (linear change) – Type I EPS -1.5 % (linear change) – Type II EPS
Limiting Oxygen Index	ASTM D2863	>24 % - Type I EPS >24% - Type II EPS
Flame Spread Rating	CAN ULC S102.2	Type I (25mm) – Frame Spread 225 (rating >25 but <500) Type II (50mm) – Frame Spread 200(rating >25 but <500)

09252

FLEXLITE SELECT EPS INSULATION BOARD
Drained Expanded Polystyrene Insulation Board Residential Application

Packaging	Durex® Flexlite Select EPS Insulation Board is supplied by the sheet. Individual sheets are bundled in polyethylene bags, to a volume of approximately 480 board feet per bundle. (One board foot is the nominal quantity of insulation derived from a piece of EPS 1 inch thick and 1 foot wide by 1 foot long). Dimensionally, each bundle is 1220 mm (4 ft) x 1200 mm (4 ft) x 762 mm (2 ½ ft). All packaging shall be UV resistant, clearly have the name Durex® printed on the bags and be labeled indicating conformance to the governing codes and tolerances required by Durex®. All insulation products for use in Durex® EIFS Systems shall be purchased from Durabond Products Limited or one of its authorized distributors. Insulation boards which are purchased from non-approved sources will void any applicable product or system warranties. Consult with Durabond for a list of approved distributors and manufacturers.
Storage	Store Durex® Flexlite Select EPS Insulation Board in a dry, vented, waterproof location and stacked off the ground. Keep materials dry, protected from rapid temperature changes, dampness and moisture and away from direct sunlight.
Application	Durex® Flexlite Select EPS Insulation Board is always installed with the 610 mm (2 ft) side running vertically and the 1220 mm (4 ft) side running horizontally and in a running bond pattern. All corners are to utilize an interlocking pattern. Follow specific procedures as outlined in the system specification. Do not place insulation onto an uncured water-resistive barrier (WRB). Any mechanical fasteners shall be of a type and size approved by Durabond Products Limited for use with the specific EIFS System being used.
Limitations	Durex® Flexlite Select EPS Insulation Board is not recommend for use: <ul style="list-style-type: none"> • Is not recommended for uses where sustained temperatures will exceed 165°F • Avoid contact with chimneys, steam pipes, electrical or sauna heaters or other such surfaces • Precautions should be taken when insulation is in contact with the soil to prevent hidden entry through the foam by vermin or insect pests
Health and Safety	For information and advice on the safe handling, storage and disposal of chemical products, refer to the most recent SDS sheet containing physical, environmental, toxic and other safety/materials handling data. For industrial use only. Keep out of reach of children.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Products Ltd. sales representative.

DURabond

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01