

Durex® Epotel SL

Self Levelling Epoxy Resin for use in Duracrete SL System

Description	Durex® Epotel SL Self Leveling Epoxy Resin is a pigmented, self-leveling epoxy compound designed to be mixed with Duracrete SL filler as part of the Duracrete SL System. Duracrete SL is designed to renovate worn concrete floors or protect new concrete against heavy wear and chemical spills. Durex® Duracrete SL Self Leveling Epoxy Surfacing can be installed as a self-sealing system, broadcast with silica and resealed to produce a solid-colored texture system, or broadcast with multicolored quartz aggregates and sealed with a clear sealer to product a decorative surface.
Uses	Durex® Epotel SL offers excellent workability designed specifically to be mixed with Duracrete SL aggregate for an easy to use, long-term, low maintenance service for heavy industrial, commercial and institutional flooring applications.
Ideal For	<ul style="list-style-type: none"> • Clean rooms • Areas that produce light manufacturing and assembly • Warehouses, workshops, mechanical rooms and laboratories • Variety of commercial and retail applications
Features	<ul style="list-style-type: none"> • Economical and durable flooring system • Excellent color retention • Fast and easy installation • Excellent abrasion and wear resistant • Will not support growth of fungus or bacteria • CFIA Approved & USDA compliant for use in federally inspected meat and poultry plants

TECHNICAL DATA (Mixed with Duracrete SL Aggregate)

PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Compressive Strength @ 7 days	ASTM C 579	11,000 psi
Tensile Strength	ASTM C 307	2,050 psi
Flexural Modulus	ASTM D790-86	550 psi
Bond Strength	ACI 503R	350 psi concrete fails
Thermal Coefficient of Expansion	ASTM D 696	0.000046 inch per inch per 0°F
Abrasion Resistance CS-17 wheel, 1 kg. load, 1000 rev.	ASTM D4060	0.1 gm. maximum weight loss
Thermal Shock Resistance	ASTM C 884	Passes
Water Absorption	ASTM C 413	0.1%
Flammability	ASTM D 635	Self-extinguishing
Impact Resistance	MIL D-3134F	16 foot-pounds concrete fractures
Indentation	MIL D-3134F	No indentation
Coverage Rate		2.0 Kg/m ² /mm Kit Size = 10kg liquids + 10 kg filler Approx. Coverage: 6.7m ² per 20 kg mix @ 1.5mm

Packaging Durex® Duracrete SL Self Levelling Epoxy Surfacing System is packages as follows: Durex® Epotel SL is packaged as a kit (Part A and Part B) in 10kg units. To be mixed with 10kg bag Duracrete SL Filler. This product is available in multiple standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the *Durex® Colour Selection Guide* for all available colour options.

Storage Conditions For improved performance, Durex® Duracrete SL should be sealed and kept in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 10 degrees C and below 35 degrees C. KEEP FROM FREEZING.

Surface Preparation	Concrete must be shot blasted and prepared to ICRI CSP 3. Do not apply this or any impermeable finish over an on-grade slab with high moisture or relative humidity levels. Prime surface with Durex® Epotel Multi-Prime or Durex® Epotel GSC. Consult Durabond for complete details.
Application	<p>Durex® Duracrete SL Self Levelling Epoxy Surfacing is installed at a nominal 60 mils to 80 mils (1.5 – 2mm) thickness consisting of a 100% solids epoxy primer; a self-leveling epoxy-silica mixture; and optional aggregates and seal coats for specified finish and texture.</p> <p>Refer to Duracrete SL system data sheet for application instructions and for all information prior to use this product. Premix components, blend Durex® Epotel SL Parts A and B with a low speed drill for 2 minute. Add Durex® Duracrete SL Filler, blending for an additional minute ensuring the aggregate is fully wetted. Pour onto floor surface in ribbons and level with a squeegee or cam rake, de-aerating with a spike roller.</p>
Limitations	Substrate must be sound, clean, properly prepared and free from hydrostatic pressure and high levels of moisture vapour transmission. As is the case with any impermeable floor coating, any concrete slab on grade to receive this product should be tested for moisture content. Product should only be installed if moisture content falls within acceptable range. Please consult Durabond for additional information.
Health and Safety	Use under well ventilated conditions with appropriate NIOSH approved respirator for silica fume and rubber gloves when handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Harmful if swallowed. Keep product out of reach of children. Read published Safety Data Sheet prior to handling and using the product.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd. sales representative.



HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

[INFO@DURABOND.COM](mailto:info@durabond.com)

[WWW.DURABOND.COM](http://www.durabond.com)

1.877.DURABOND (387.2266)

V2.01