

Durex® Komfort Primer

100% Solids Urethane Flooring Primer for Comfort Flooring Systems

Description	Durex® Komfort Primer 100% Solids Urethane Flooring Primer is a two-component, polyurethane-based flooring primer. It is specially formulated to perform where substrate penetration and superior adhesion is required.
Uses	Durex® Komfort Primer is used to seal and prime concrete and wood substrates to be top-coated with various coatings systems. Durex® Komfort Primer is mainly used as a primer for Durex® Komfort Ergonomic Flooring Systems and other related coatings to assist in the reduction of out-gassing and to achieve ultimate adhesion. Komfort Primer performs as a protective primer for comfort flooring (ergonomic) related applications. Must be top-coated, unless indicated otherwise.
Ideal For	<ul style="list-style-type: none"> • Versatile protective floor primer • Concrete and wood primer for polyurethane, epoxy and acrylic coatings • Primer for Comfort flooring coatings, systems and membranes • Metal surfaces • Food processing and pharmaceutical plants
Features	<ul style="list-style-type: none"> • Excellent adhesion to a variety of substrates • Good physical properties • Outstanding stability at low temperatures • Zero VOCs, 100% solid urethane • Excellent moisture resistance • High-build capability (up to 400 microns, 16 mils) • Smooth, bubble-free film surface • Superior substrate penetration; seals the surface • CFIA approved

TECHNICAL DATA

PHYSICAL PROPERTIES

Colour	Clear - Amber
Resin Type	Aromatic urethane – Hybrid Polyol
Mix Ratio	As supplied in kit
Part A (Resin):Part B (Urethane)	
Cure Time @ 5-23°C	To touch: 12 hours To recoat: 5-24 hours Fully cured: 7 days
Coverage	5.0 m ² /L (200 ft ² /US gal) @ 8 mils DFT
Recommended Film Thickness	5 mils (75 µ)
Pot Life @ 23°C (75°F)	35-45 minutes
Reducer/Clean-Up	Lacquer thinner or IPA
V.O.C.	Zero

PERFORMANCE PROPERTIES

TEST METHOD

RESULTS

Percent Solids	ASTM D7232-06	100%
Viscosity (Brookfield) 23°C (75°F) A+B	ASTM D2196	700-800 cps
Abrasion Resistance	ASTM D5178-91, CS-17 wheel	35 mg, 1000 g load, 1000 cycles
Tensile Modulus	ASTM D638-86	2,400 psi
Elongation	ASTM D638-86	45%
Specific Gravity	ASTM D333	1.10 ± 0.05 g/L 8.90 ± 0.1 lb/gal
Flexural Modulus	ASTM D790-86	47,000 psi

Packaging	Durex® Komfort Primer is packaged in a 20kg kit (Parts A & B).
Storage Conditions	Store Durex® Komfort Primer in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 10 degrees C and below 35 degrees C. KEEP FROM FREEZING.
Surface Preparation	<p>Concrete, wood and metal surfaces must be dry, free of dirt, oils, and any other contaminants that may prevent proper adhesion. Contact Durabond Technical Services for surface preparation methods of surfaces contaminated by oil or other materials.</p> <p>Concrete: New concrete shall be allowed to cure for a minimum of 28 days and have a compressive strength of concrete of at least 25 MPa (3,625 psi) before coating. Moisture content of the concrete shall be less than 4% by weight prior to application or the substrate must be primed with Durex® Epotel 100 Moisture Block. Contact a Durabond Technical Representative for further assistance. Prepare surfaces by shot-blasting to achieve a surface consistent with ICRI CSP 3-4.</p> <p>Wood: Wood surfaces must be free of dirt and other contaminants that may prevent proper adhesion. Treat wood joints with polyurethane sealant.</p> <p>Metal: Metal must be cleaned of all dirt, debris and rust prior to application.</p>
Mixing Instructions	Mixing shall be carried out in a clean, rust-free container, and mixed by a power drill at 400-500 rpm maximum. Do not mix Part A and Part B together until ready for application, only mix materials to be used within working time window. Mix Part A and Part B together slowly, using a low-speed drill for a minimum of 2 minutes, ensuring that both components are thoroughly mixed and there is a consistent colour without any residue remaining on the sides of the pail. Extra care must be taken to avoid introducing air into the mixture.
Application	Use a good-quality synthetic brush (75-100 mm [3-4 in.] brush length) to paint edges where the floor meets the walls. Then use a lint-free 12.7 mm (1/2 in.) nap roller cover and 230 mm (9 in.) frame to apply an even coat of Durex® Komfort Primer. Maintain a wet edge to prevent overlap and gloss differences.
Clean-Up	Wash all tools and equipment immediately with mineral Xylene or solvent-based cleaner. Allow any unused product to harden in container and discard according to local regulations.
Limitations	Do not apply Durex® Komfort Primer if ambient and substrate temperature is less than 10 degrees C or above 32 degrees C during application and curing time. Apply topcoat or subsequent coat within 24 hours. Always adhere to published recoating schedules to ensure coating adhesion. Product must be applied in temperatures 3 degrees C above the dew point. Moisture content of the concrete must be less than 4% by weight, if not the surface must be primed with Durex Epotel Moisture Block 100. Do not add solvent to the mixture.
Health and Safety	Use under well-ventilated conditions with rubber gloves when handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Extremely harmful if swallowed. Do not induce vomiting. Keep product out of reach of children. Read published Material Safety Data Sheet for additional information.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd sales representative.

DURabond

Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01