

Durex® Dur-A-Comfort Topcoat

High-Durability, UV-Resistant Aliphatic Polyurethane Topcoat for Comfort Floors

Description	Durex® Dur-A-Comfort Topcoat High-Performance UV-Resistant Polyurethane Flooring Topcoat is an aliphatic, water-based, thin-build, liquid-applied urethane coating. This highly durable, high performing formulation offers excellent abrasion and UV resistance for colour and gloss stability for decorative resinous flooring and wall systems.
Uses	Durex® Dur-A-Comfort Topcoat High-Performance UV-Resistant Polyurethane Flooring Topcoat is a roller-applied protective topcoat for the Durex® Dur-A-Comfort line of flooring systems. Durex® Dur-A-Comfort floor systems are used in a wide range of institutional, commercial, residential and recreational floor applications where seamless, ergonomics, long-term durability, UV and abrasion resistance is required.
Ideal For	<ul style="list-style-type: none"> · Top-Coat for Durex® Dur-A-Comfort floor systems · Institutional, Commercial and Recreational resinous flooring topcoat · Health Care and Pharmaceutical Applications (Including Clean Rooms)
Features	<ul style="list-style-type: none"> · Water-based, aliphatic polyurethane · Water based, easy to apply · Resistant to weathering and colour fade by UV rays · Wide-service temperature range · Excellent abrasion and impact resistance · Good flow and leveling properties for finishing · Non-staining chemical resistance · Available in different finishes: Gloss, Semi-gloss, Satin and Matte · Available in non-slip additive · Low VOC, Low Odour. · Available in virtually any colour

TECHNICAL DATA

PHYSICAL PROPERTIES		
Colour	Pigmented (Finishes: Gloss, Semi-gloss, Satin & Matte)	
Resin Type	Aliphatic Polyurethane/Acrylic	
Coverage	5.9 m ² /L (250 ft ² /US gal) @ 3 mils DFT Note: 2 coats recommended for best results	
Cure Time @ 23°C (75°F)	To touch: 30 minutes Foot traffic: 8 hours Fully cured: 7 days	
Pot Life	2 hours	
Mixing Ratio	6:1	
V.O.C.	< 65 g/L	
PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	48 ± 5% (vol.)
Viscosity (Brookfield) 23°C (75°F)	ASTM D2196	500 cps
Abrasion Resistance	ASTM D4060-01	100 g load, 1700 cycles C-S wheel: 20 mg loss
Hardness (Pencil)	ASTM D3363	2H
Hot Water Immersion	ASTM D870	Pass – no blisters after 500 hours @ 38°C (100°F)
QUV Weathering	ASTM G 154 CYCLE 7	Complete Pass 1000 hours
Impact Test	ASTM D2794	Pass direct/indirect 56 in.-lb
Sheen (60°)	ASTM D3679	Gloss: 80-85% Semi-gloss: 40-70% Low sheen: 5-20%
Specific Gravity	ASTM D333	1.03 ± 0.01 g/L 8.6 ± 0.05 lb/gal
Coefficient of Friction	ASTM D2047-17	Satin: Dry: 0.78 / Wet: 0.63 Gloss: Dry: 0.77 / Wet: 0.56

Packaging	Durex® Dur-A-Comfort Topcoat High-Performance UV-Resistant Polyurethane Flooring Topcoat is packaged in 18.9 L (5 gal) and 3.78 L (1 gal) kits. This product is available in gloss, semi-gloss, satin and matte and with a fine non-slip additive.
Storage Conditions	Store Durex® Dur-A-Comfort Topcoat High-Performance UV-Resistant Polyurethane Topcoat in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials in ambient temperatures above 10 degrees C and below 35 degrees C. KEEP FROM FREEZING.
Surface Preparation	Coated Floor Surfaces: Coated surfaces shall be clean, dry, and structurally sound and free of debris or other materials deleterious to adhesion, including amine blush. Mechanical abrasion is required for surfaces that have been coated for more than 24 hours. Previously coated surfaces shall be well bonded and free of any material that may impede adhesion. Sand and solvent wipe. Contact Durabond for technical information and assistance.
Mixing Instructions	Durex® Dur-A-Comfort Topcoat is supplied in a 2 part kit, with Part A (resin) and Part B (Catalyst) Durex® Dur-A-Comfort Topcoat is to be mixed with a non-air entraining, low speed (300-400rpm) electric mixer. Gently mix part A, slowly pour the Part B into the vortex and mix for at least three (3) minutes. Do not entrain air and keep the mixing paddle inside the mixture at all times. Pot life of coating is approximately 2 hours at 23 degrees C (75 degrees F). For best results apply Durex® Dur-A-Comfort Topcoat immediately.
Application	Erect suitable barriers to prevent through traffic or other trades from entering working area during installation of floor coating and protect adjacent surfaces from damage. Provide adequate ventilation, and maintain a dust-free environment for the duration of work. Prepare a test patch to verify the effectiveness of the cleaning process and check product adhesion. Durex® Dur-A-Comfort Topcoat can be applied using a lint-free roller, spray gun or brush. Use a good-quality synthetic brush (75-100 mm) to paint floor edges first. Use a lint-free 12.7 mm (1/2 in.) nap roller to apply an even coat of Durex® Dur-A-Comfort Topcoat. Maintain a wet edge to prevent overlap marks and gloss differences. Use an airless paint spray gun for spray applications. Multiple coats of Durex® Dur-A-Comfort Topcoat can be applied for increased protection. Multiple coats must be applied within 24 hours of completion of the previous coat. Floor must be sanded and solvent wiped if the recoat window is exceeded. Contact Durabond Technical Services for further information. Note: Drying time of Durex® Dur-A-Comfort Topcoat is dependent on temperature and humidity. Lower temperatures with high humidity levels will result in a longer drying time. For best results apply materials when ambient temperatures are above 15 degrees C.
Cleaning	Regular cleaning will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Contact Durabond Technical Services for further information.
Limitations	Do not use this product if substrate and ambient temperature is less than 15 degrees C or more than 30 degrees C, and/or if relative humidity is greater than 75%. Floor must be 3 degrees C above dewpoint. Durex® Dur-A-Comfort Topcoat High-Performance UV-Resistant Urethane Flooring Topcoat is not recommended to be used in a wet environment. Continuous pressurized water washing is not recommended. Indoor use only.
Health and Safety	Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical advice if irritation occurs. Harmful if swallowed. Keep product out of reach of children. Read published Material Safety Data Sheet prior to storage, handling and use.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd sales representative.



Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01