

Durex® Uraflex 360 NP

Primerless Elastomeric Traffic-Bearing Polyurethane Waterproofing Membrane

Description	Durex® Uraflex 360 NP is a Primerless, Elastomeric Traffic-Bearing Polyurethane Waterproofing Membrane. Durex® Uraflex 360 NP is a two-component, high solids, extremely elastomeric polyurethane waterproofing membrane that maintains flexibility in freezing temperatures. Durex® Uraflex 360 NP adheres to concrete and wood surfaces to form a highly effective waterproofing membrane. It must be top coated with a Durex® Traffic-Bearing Coating to achieve an effective Traffic-Bearing System.
Uses	Durex® Uraflex 360 NP is a Primerless elastomeric, polyurethane-based waterproofing membrane that is used in conjunction with other Durex® Traffic-Bearing coatings to form a comprehensive, traffic-bearing, waterproofing system. It is designed to perform as a water-resistant traffic-bearing membrane on a variety of surfaces such as concrete and wood. Capable of bridging cracks up to 1/16 of an inch with excellent flexibility in cold temperatures.
Ideal For	<ul style="list-style-type: none"> Balcony terraces and pedestrian walkways Parking decks Mechanical rooms Plaza, pool and recreational decks, and vehicular ramps Stadiums, Shower Rooms and related Institutional Applications
Features	<ul style="list-style-type: none"> Outstanding water impermeability sealing properties Highly penetrable Very low VOCs Primer-free, tenacious substrate adhesion High chemical resistance to acids, alkalis, salts, seawater, sewage and other compounds Fast-curing properties Excellent low temperature flexibility and crack-bridging properties ASTM C957 (CAN/CSA-S413-07) Compliant

TECHNICAL DATA

PHYSICAL PROPERTIES	
Colour	Light Grey
Resin Type	Polyurethane
Mix Ratio	Part B: Part A 4:1 by volume
Cure Time @ 23°C	To touch: 4-6 hours To recoat: 8-12 hours Traffic: 24 hours
Coverage	80 ft²/gal @ 20 mils DFT
Pot Life @ 23°C	15-20 minutes

PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	99%
V.O.C.	ASTM D3960	4-5 g/L
Specific Gravity	ASTM D333	1.19 ± 0.05 g/L
Mixed Viscosity	ASTM D2196	3300 cps
Abrasion Resistance	ASTM D5178-91, CS-17 wheel	75 mg, 1000 g load, 1000 cycles
Tensile Strength	ASTM D412	2,500 psi
Adhesion to peel	ASTM C 957	Pass
Elongation	ASTM D412	900%
Crack bridging	ASTM C 957	Pass (no crack)
Low Temperature Flexibility	1/8" Mandrel @ -26°C	Pass
Water Absorption	ASTM D570	0.25%
Shore A Hardness	ASTM D2240	67
Pull-Off Strength of Coatings	ASTM D4541	2.71 MPa (400 psi) failure at concrete
Water Vapour Transmission	ASTM E96 – Procedure B	0.05 grain/hr·pi² 0.029 g/hr·m²
Water Vapour Permeability	ASTM E96	0.20 Perm In. 0.0025 ng/Pa·s·m²
Water Vapour Permeance	ASTM E96	4.70 x 10 - 5 perm 0.028 ng/ Pa·s·m²

Packaging	Durex® Uraflex 360 NP Primerless is packaged in 18.9 L (5 gal) and 3.78 L (1 gal) kits.
Storage Conditions	Store Durex® Uraflex 360 NP Primerless in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store between 10°C and 25°C. KEEP FROM FREEZING.
Surface Preparation	<p>Concrete, wood and metal surfaces must be dry, free of dirt, oils, and any other contaminants that may prevent proper adhesion. Contact Durabond Technical Services for surface preparation methods of surfaces contaminated by oil or other materials.</p> <p>Concrete: New concrete shall be allowed to cure for a minimum of 28 days and have a compressive strength of concrete of at least 25 MPa (3,625 psi) before coating. Moisture content of the concrete shall be less than 4% by weight prior to application or the substrate must be primed with Durex® Epotel 100 Moisture Block (up to 6%). Contact a Durabond Technical Representative for further assistance. Prepare surfaces by shot blasting to achieve a surface consistent with ICRI CSP 3-4. Treat all cracks as per ASTM C1127. Correct concrete repairs with Durex® Duracrete Trowel. Not applicable for on-grade slab applications. Extremely porous substrates must be primed with Durex® Uraflex Primer for best results.</p> <p>Plywood: Plywood must be minimum thickness of 1/2 inch exterior grade plywood secured and fastened solid to support substrates. Surfaces must be free of dirt and other contaminants that may prevent proper adhesion. Treat plywood joints with polyurethane sealant and Durex® Barrier Seam Tape laid in a bed of Durex® Uraflex 360 NP Primerless Elastomeric Polyurethane Waterproofing Membrane.</p> <p>Metal: Metal must be cleaned of all dirt, debris and rust prior to application.</p>
Mixing Instructions	Mixing shall be carried out in a clean, rust-free container, and mixed by a power drill at 400-500 rpm maximum. Do not mix Part A and Part B together until ready for application, only mix materials to be used within working time window. Mix full kit as provided of Part A resin with Part B urethane. Mix Part A and Part B together slowly, using a low-speed drill for a minimum of 5 minutes, ensuring that both components are thoroughly mixed and there is a consistent colour without any residue remaining on the sides of the pail. Extra care must be taken to avoid introducing air into the mixture.
Application	Apply Durex® Uraflex 360 NP with a notched squeegee at a uniform thickness of 20 mils DFT (or as specified) to form an effective waterproofing membrane. Measure wet film mil thickness with a thickness gauge. Allow membrane to cure for at least 8 hours prior to application of topcoat. Substrate temperature must be at least 3 degrees Celsius above dew point prior to application. Warm, humid environments will cure more rapidly. Ensure that the product is slightly tacky to the touch prior to installation of the topcoat. Specified Durex® Topcoat must be applied within 24 hours of application. Consult with Durabond Technical Services for further information.
Limitations	Do not apply Durex® Uraflex 360 NP Elastomeric Polyurethane Traffic-Bearing Topcoat if ambient and substrate temperature is less than 6 degrees C or above 32 degrees C during application and curing time. Topcoat with Durex® Uraflex 361, Durex® Uraflex 362 or Durex® Uraflex 375UV within 24 hours. Always adhere to published recoating schedules to ensure coating adhesion. Product must be applied in temperatures 3 degrees C above the dew point. Moisture content of the concrete must be less than 4% by weight, if not the surface must be primed with Durex® Epotel Moisture Block 100 (up to 6% - Consult Durabond). Do not add solvent to the mixture.
Clean-up	Wash all tools and equipment immediately with mineral Xylene or solvent-based cleaner. Allow any unused product to harden in container and discard according to local regulations.
Health and Safety	Use with proper protective equipment when using/handling the product. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water and seek medical attention if irritation occurs. Keep product out of reach of children. Read published Material Safety Data Sheet prior to handling and use.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd. sales representative.

DURabond

Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01