

Durex® Dur-A-Comfort REG System

Ergonomic & Seamless Polyurethane Resilient Floor System (3mm)

Description	Durex® Dur-A-Comfort REG System is an ergonomic, soft-touch resilient seamless polyurethane-based flooring system specifically engineered for human comfort. Durex® Dur-A-Comfort REG is designed for high-traffic areas where an ergonomic, high point load resistant solution is desired. The system consists of a primer, 3mm thick decorative self leveling soft touch layer and a finishing sealer (matte or eggshell finish). Installed at 3 mm (120 mils) thick, the Durex® Dur-A-Comfort REG System offers excellent abrasion resistance for demanding floor areas. Available in solid colour (standard finish) or multi-effect finishes (DecoArt).
Uses	Durex® Dur-A-Comfort REG System is used as decorative and protective ergonomic flooring system for dry areas that will be exposed to higher traffic where sound absorption is not as critical. It is best used for institutional, commercial, and retail flooring applications where high a seamless flooring system is required.
Ideal For	<ul style="list-style-type: none"> . Laboratories . Hospital Main Corridors (dry areas) . Retail, Office and Commercial Applications . Recreational facilities . Public institutions and buildings
Features	<ul style="list-style-type: none"> . Ergonomic and Seamless . Available in a multitude of colours and decorative finishes (DecoArt) . High performance, aesthetically pleasing, durable finish . Easy and quick to install . Long term service life . Easy to recoat and repair . Lightweight seamless flooring system, easily upturned to create curbs and containment areas . Will not support growth of fungus or bacteria . Excellent abrasion and slip resistance . Easy to clean and to maintain . CFIA approved and USDA accepted

TECHNICAL DATA

PHYSICAL PROPERTIES							
Colour	Standard Finish: Solid Colour. DecoArt Finish: Variety of Designs & Colours						
Coverage	<table border="0" style="width: 100%;"> <tr> <td style="background-color: #f2f2f2;">Durex® Dur-A-Comfort Primer</td> <td>5 m²/L (200 ft²/gal) @ 8 mils</td> </tr> <tr> <td style="background-color: #f2f2f2;">Durex® Dur-A-Comfort Self-Leveling</td> <td>Durex® Dur-A-Comfort Self Leveling (or Durex® Dur-A-Comfort DecoArt: 3.0kg/m² (45 ft²/kit) @ 3mm (120 mils)</td> </tr> <tr> <td style="background-color: #f2f2f2;">Durex® Dur-A-Comfort Top Coat</td> <td>0.1 kg/m² (400 ft²/gal) @ 3 mils WFT (2 coats required)</td> </tr> </table>	Durex® Dur-A-Comfort Primer	5 m ² /L (200 ft ² /gal) @ 8 mils	Durex® Dur-A-Comfort Self-Leveling	Durex® Dur-A-Comfort Self Leveling (or Durex® Dur-A-Comfort DecoArt: 3.0kg/m ² (45 ft ² /kit) @ 3mm (120 mils)	Durex® Dur-A-Comfort Top Coat	0.1 kg/m ² (400 ft ² /gal) @ 3 mils WFT (2 coats required)
Durex® Dur-A-Comfort Primer	5 m ² /L (200 ft ² /gal) @ 8 mils						
Durex® Dur-A-Comfort Self-Leveling	Durex® Dur-A-Comfort Self Leveling (or Durex® Dur-A-Comfort DecoArt: 3.0kg/m ² (45 ft ² /kit) @ 3mm (120 mils)						
Durex® Dur-A-Comfort Top Coat	0.1 kg/m ² (400 ft ² /gal) @ 3 mils WFT (2 coats required)						
Mix Ratio	Refer to Product TDS Sheet						
Pot Life	Refer to product TDS Sheet						
Chemical Resistance	Contact Durabond for specific information						

PERFORMANCE PROPERTIES	TEST METHOD	RESULTS
Percent Solids	ASTM D7232-06	100%
Shore Hardness A	ASTM D2240	83
Sound Dampening		4 db
Suitable for Underfloor Heating		Yes
Abrasion Resistance	ASTM D4060	(-0.04g) C5-17/1000 rotations/ 1000g
Impact Strength	ASTM D4226	167 in./lbs.
Residual Impression	ASTM D4226	0.05mm (360kg load)
Tensile Strength	ASTM F970	1,454 psi. (~ 10.0 N/mm ²)
Tensile Adhesion Strength	ASTM D4541	> 500 psi. (3.5 MPa) (concrete failure)
Tear Strength	ASTM D624	153.36 lb./in. (~ 27 N/mm 14 days)
Elongation at Break	ASTM D412	195%
Crack Bridging Ability	ASTM C1305	Passed
External Fire Performance	ASTM E648	Class I
Gloss Level	ASTM D-523	10 (60 Degree)
Coefficient of Friction	ANSI 326.3	0.6

Packaging Durex® Dur-A-Comfort REG System is packaged separately per individual product. This product is available in multiple standard colours. Custom colour matching can also be attained at an additional cost. Please refer to the respective Durex® Dur-A-Comfort *Colour Selection Guide* for all available colour options.

Storage Conditions Store Durex® Dur-A-Comfort REG System in a dry, vented, waterproof location, stacked off the ground, out of direct sunlight and other detrimental conditions. Store liquid materials as ambient temperatures above 10 degrees C and below 35 degrees C. **KEEP FROM FREEZING.**

Surface Preparation Concrete substrate must be prepared to ICRI CSP 3. For best results surfaces shall be mechanically abraded and be sound, clean, properly prepared, and free from hydrostatic pressure and high levels of moisture vapour transmission. Do not apply this or any impermeable finish over an on-grade slab with moisture levels above 4% by weight (Durex® Eptel Moisture Block may be used for moisture content up to 6%, always consult your Durabond representative prior to use). Repair floor areas with Durex® Duracrete Trowel or Durex® Dur-A-Patch RS-45. Integral cove base shall be installed prior to flooring. Contact Durabond for any questions.

Application Durex® Dur-A-Comfort REG System is installed at a nominal 3 mm 120 mils thickness; consisting of a special primer, Durex® Dur-A-Comfort Primer; a high-quality self leveling ergonomic later, Durex® Dur-A-Comfort Self Leveling and a high-performance sealer Durex® Dur-A-Comfort Top Coat. A variety of top coat components can provide a solid or decorative colour scheme in, matte or eggshell. Slip resistance can be enhanced with the addition of Level 4, ultra fine anti-slip.

Step 1 PRIMER: Durex® Dur-A-Comfort Primer. Premix components A and B with a low-speed drill equipped with a non-air entraining paddle mixing blade for two minutes. Pour onto substrate in ribbons and apply with squeegee. Cut in with brush, and back roll with a short nap roller. Do not allow material to pond. Shall be applied to a thickness of 8 mils, but will vary depending upon the condition of the substrate.

Step 2 DECORATIVE SELF LEVELING LAYER: Within a 24-hour period, apply Durex® Dur-A-Comfort Self Leveling or Durex® Dur-A-Comfort DecoArt, refer to the respective Technical Data Sheet for mixing and application instructions. Once mixed, apply Durex® Dur-A-Comfort Self Leveling at a thickness of 3mm.

Step 3 TOP COAT: Within a 24-hour period, apply Durex® Dur-A-Comfort Top Coat (or recommended) refer to the respective Technical Data Sheet for mixing and application instructions. Apply two coats. For additional anti-slip add recommended slip resistant aggregate. Contact a Durabond Technical Representative for details.

Care & Maintenance	Newly installed floors should be cured a minimum of 48 hours at 20°C (70°F) before wash-downs. Only warm water should be used to clean within the first week. If the use of a detergent is absolutely necessary during the first week, use a non-chlorine cleaner dissolved in water. Good housekeeping practices and regulated spill removal will prolong the service life of the floor. While polymer flooring often requires less maintenance than other finishes, cleaning and stain removal must be performed. Stains should be removed as soon as possible.
Limitations	Durex® Dur-A-Comfort REG System is impermeable. Test all concrete slabs on grade for moisture content. Product should only be installed if moisture content falls within an acceptable range. Minimum application temperature is 8°C (45°F). Below 15°C (62°F), handling characteristics are affected, and cure times are lengthened. Chemical exposure, service temperatures, mechanical abuse, and housekeeping influence service life. The project depending on chemical exposure may require Durex® Chemical Resistant Coatings. For installations exposed to UV, the self-leveling coat is to be replaced with a UV resistant coating. Please consult your Durabond Technical Representative for further details.
Health and Safety	Read and follow the Safety Data Sheet prior to use. Avoid contact with eyes and prolonged contact with skin. Wear protective clothing and face protection at all times while handling, mixing and applying the products. If contact occurs, flush immediately and seek medical advice if irritation occurs. Extremely harmful if swallowed. Keep product out of reach of children. Read published safety data sheets for additional information.
Warranty	Durabond warrants this product is free of manufacturing defects, and will replace at no charge, provided it has been applied within 12 months of purchase, it has been installed for uses suitable for this product and in accordance with the manufacturer's instructions.
Technical Services	Technical support is available upon request at info@durabond.com . For the latest version of this data sheet, please visit our website at www.durabond.com , call toll free at 1-877-DURABOND (387-2266) or speak with your Durabond Technical Coatings Ltd. sales representative.



Technical Coatings Ltd

HEAD OFFICE
55 Underwriters Road
Scarborough, ON M1R 3B4
T 416.759.4474 F 416.759.4470

MISSISSAUGA
6178 Netherhart Road
Mississauga, ON L5T 1B7
T 905.565.9283 F 905.565.9365

EDMONTON
14345 120th Avenue
Edmonton, AB T5L 2R8
T 780.451.6364 F 780.453.9056

INFO@DURABOND.COM

WWW.DURABOND.COM

1.877.DURABOND (387.2266)

V2.01